RG104 E-1 Box 121

20

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.	Gain. OZ.	DEC.	Description of Bullion.
May 10th	762	Mrs. M. Lee	58	06	58	01		05	09			Bar
	3	G. G. Thompson	22	64	21	45	1	16	5 04			Jewelry, Mish. Cases & Bars
	4	Do Bennett 13.65	16	54	13	61	2	93	17 24			Jewelry
	5	Do	7	42	7	14		28	4 00			Jewelry & Mish Cases
	6	Do	37	49		38		11	30			Bullion & Bars
	7	Do	21	54	18	89	2	65	12 05			Jewelry
	8	Do	37	77	22	00	5	77	20 61			Jewelry, Mish. Cases & Scraps, 50 cts.
	9	Do	21	50	20	17	1	33	6 33			Jewelry & Mish Cases
	70	Phillips & Jacobs	53	73	53	73						U.S. Coin
11th	1	G. G. Thompson	5	48	5	28		20	4 00			Ame, N.C.
	2	Drexel & Co.	33	45	31	43	2	02	6 12			Ame & Lps, Wyoming
	3	G. A. G. Rosenthal	10	29	10	26		03	30			Ring
	4	A. Loudon Snowden, Supt.	101	36	101	33		03	03			Bars, U.S. Mint, N.C.
	5	A. J. Kelman & Co.	39	25	32	12	7	13	20 88			Leaf
12th	6	Benj. G. Hopper	7	79	7	77		02	25			Bar
	7	John Littlefield	10	67	10	01		66	6 00			D'ds, Fillings, &c.
	8	John Gartner, Cash.	7	70	7	70						Melted Lps, Va.
13th	9	G. G. Thompson	9	23	8	42		81	9 00			Button
	80	Simons, Bro. & Co.	128	84	128	70		14	11			Bars
	1	G. G. Thompson	11	77	11	17		60	5 00			Button
	2	Morgan & Keasby	42	97	38	90	14	07	32 72			Scraps & Fillings
	3	Jacob Bennett & Son	28	20	28	15		05	18			Bar
	4	J. G. White	14	94	13	69	1	25	8 33			Jewelry
	5	H. M. Phaeger & Co.	15	28	15	23		05	33			Bar, &c.
14th	6	G. G. Thompson	6	98	6	42		56	8 00			Ame & Lps, N.C.
	7	Do	12	39	11	88		51	4 25			Mish Cases & Jewelry
	8	Morgan, Keasby & Co.	107	45	107	45						U.S. Coin
	9		75	88	75	90				02		Bars, U.S. & C.N.C.
15th	90	G. G. Thompson	5	80	5	79		01	17			Melted Lps, Va.
	1	Do	14	07	10	45	3	62	25 86			Jewelry, Mish. Cases, &c.
	2	Do	36	05	33	16	2	89	8 03			Jewelry, Mish Cases, Scraps, &c.
	3	H. Muhr's Sons	17	79	17	79						Bars
	4	Drexel & Co.	13	22	10	94	2	28	17 54			Lps, Grs & Sand, Va.
	5	Richd Helms	26	86	26	86						U.S. Coin
	6	Phillips & Jacobs	53	71	53	71						U.S. Coin
			1104	11	1052	92	51	31	1 12	112		

Rates of Melter & Refiner.

5/19/80

The deposits are from the following sources:

Virginia (2)	3
N. Carolina (2)	4
Wyoming ___	1
Finer bullion (4)	8
Jewelry &c.	12
Very base	3
Coin	4
Total	35

The loss in melting the mixed deposits from N. Carolina = 6 %, and that from Wyoming, 6.12 %, is in each case reasonable; as is also that of 17½ % from Virginia, because of the liberal admixture of sand. The loss of 0.15 % on finer bullion is a fair average, the highest being only 0.33 %; the loss of 10.35 % on jewelry & similar bullion is moderate; that of 24¾ % on the very base bullion is but reasonable. Much more unreasonable is the loss of nothing in melting the 250 oz. of coin.

Jas C Booth
M & R

For week ending May 15th 1880
Approximate value, $ 16,320.26

To the Director of the Mint.

J. Ashley Douglass
Register.

RG104 E-1 Box 121

Report of Gold Deposits
melted for week ending
May 15th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending: -

May 15, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]